


# SOFT TONE



## PRODUCT DETAILS

Surface structure Slightly Brushed  
Finish Osmo PolyX + Osmo PolyX top-coating

### Engineered Wood - 14/3 mm - T&G



**SINGLE STRIP**  
• 2V  
• L: 85% m<sup>2</sup> 1720 + max. 2400, 15% m<sup>2</sup> 500-1520 mm




**HERRINGBONE**  
• 4V  
• 100/120 x 600 or 175 x 700 mm



**CHEVRON\*\***  
• 4V  
• 100 x 600 mm  
\*\*T&G insert required

Grading	Width (mm)		
	190	225	245
Special Rustic	•	•	•
Original	•	•	•
Calm	•		
Superb	•		
Elegance	•		
Superb/Elegance		•	•

### Solid Wood - 20 mm - T&G



**SINGLE STRIP**  
• 2V  
• L: 85% m<sup>2</sup> 1720 + max. 2400, 15% m<sup>2</sup> 500-1520 mm



**HERRINGBONE**  
• 4V  
• 100/120 x 600

Grading	120/150	170/185
	Original	•
Original		•
Superb/Elegance		•

	Test method	Request	Result	
			Solid 20mm	3-layer 14mm
Production standard & Conformity	EN 14342, EN 13489, EN 13488 EN 13629, EN 13226		Implemented	Implemented
Moisture content	ČSN EN 13183-1		9 ±2%	7 ±2%
Formaldehyde emission	ČSN EN 717-1	≤ 0,124mg/m <sup>3</sup>	E1	E1
PCP (pentachlorophenol)	CEN/TR 14823	≤ 5 ppm	meets	meets
Slip resistance	CEN/TS 15676		Dry ≥ 69 Wet ≥ 29	Dry ≥ 69 Wet ≥ 29
Reaction to fire	ČSN EN 13501-1		Cfl-S1	Dfl-S1
Thermal resistance	ČSN EN ISO 10456		0,15 m <sup>2</sup> · KW	0,11 m <sup>2</sup> · KW
Thermal conductivity	ČSN EN ISO 10456		0,13 W/mK	0,13 W/mK
Biological durability	ČSN EN 335-1, ČSN EN 335-2		Class 1	Class 1
Underfloor heating			Not recommended	Up to 225 mm
Recommended usage	Suitable for interior use in all project sectors: residential-commercial-hospitality-retail. Actual warranty & maintenance instructions apply			
Well-managed forests	This product is made with PEFC certified wood			

For more details, see <https://www.escoflooring.com>

ESCO General Terms and conditions apply, see <https://www.escoflooring.com>



**DECOSPAN**  
Wood Solutions