


KAREL IV



PRODUCT DETAILS

Surface structure Handcrafted
Finish ESCO oxidative oil


Engineered Wood - 14/3 mm - T&G



SINGLE STRIP
• 2V

Length (mm)	85% m ² 1720-2400mm 15% m ² 500-1520mm
Width (mm)	190
Grading	Karel IV

Solid Wood - 20 mm - T&G



SINGLE STRIP
• 2V

Length (mm)	60% m ² 1700-2400mm 40% m ² 500-1650mm
Width (mm)	170/185
Grading	Karel IV

TECHNICAL PROPERTIES

	Test Method	Solid 20mm	3-layer 14mm
Production standard & Conformity	EN 14342, EN 13489, EN 13488 EN 13629, EN 13226	Implemented	Implemented
Moisture content	ČSN EN 13183-1	9 ±2%	7 ±2%
Formaldehyde emission	ČSN EN 717-1	E1	E1
PCP (pentachlorophenol)	CEN/TR 14823	≤ 5 ppm	≤ 5 ppm
Slip resistance	CEN/TS 15676	Dry ≥ 69 Wet ≥ 29	Dry ≥ 69 Wet ≥ 29
Reaction to fire	ČSN EN 13501-1	Cfl-s1	Dfl-s1
Thermal resistance	ČSN EN ISO 10456	0,15 m ² · K/W	0,11 m ² · K/W
Thermal conductivity	ČSN EN ISO 10456	0,13 W/mK	0,13 W/mK
Biological durability	ČSN EN 335	Class 1	Class 1
Underfloor heating		Not recommended	Up to 225 mm
Recommended usage	Suitable for interior use in all project sectors: residential-commercial-hospitality-retail. Actual warranty & maintenance instructions apply		
Well-managed forests	This product is made with PEFC certified wood		

For more details, see <https://www.escoflooring.com>

ESCO General Terms and conditions apply, see <https://www.escoflooring.com>



DECOSPAN®